



KOSTER KB-FIX 5

Fast setting cement for stopping leaks

Features

KOSTER KB-Fix 5 is a fast setting waterproof and weatherproof mortar.

Technical Data

Compressive strength, 2 hours	Approx. 700 psi
Compressive strength, 7 days	> 4300 psi
Compressive strength, 28 days	> 5800 psi
Flexural tensile strength, 7 days	> 700 psi
Reaction time, 70 °F	Approx. 5 min
Application of next layer	After approx. 3 hours

Fields of Application

KOSTER KB-Fix 5 is designed for filling holes and cracks in plaster and masonry, anchoring wall anchors, anchor fittings, handrails, grates, radiators, and sealing pipe penetrations. KOSTER KB-Fix 5 can be used indoors or outdoors.

Substrate

The surface must be sound, clean, and free of oil and grease.

Application

Mix 3 parts KOSTER KB-Fix 5 with 1 part of water into a stiff, viscous mortar. When sealing or repairing larger areas, press the mortar into place using a board or trowel until it has set. In cold weather, mix KOSTER KB-Fix 5 with warm water (approx. 70 °F).

Coverage

Approx 30 lb/cubic ft.

Cleaning

Clean tools immediately after use with water.

Packaging

C 515 006	13.2 lb bucket
C 515 015	33 lb bucket

Storage

Store dry. In original sealed packages, it can be stored for approx. 6 months.

Safety

Consult Safety Data Sheet. Always wear proper personal protective equipment when handling this product.

Limited Warranty

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those

products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

Related products

KOSTER KB-FIX 1	Art.-Nr. C 511 015
KOSTER KB-Pox IN	Art.-Nr. IN 231
KOSTER KB-Flex 200	Art.-Nr. J 250
KOSTER Mautrol Liquid Sealant	Art.-Nr. M 241
KOSTER Capillary Rods	Art.-Nr. M 963
KOSTER KD System	Art.-Nr. W 219

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.