



KOSTER MPE-Color

Multi purpose pigmented epoxy

Features

KOSTER MPE-Color is a unique, versatile, modified cycloaliphatic multi-purpose pigmented epoxy. KOSTER MPE-Color is a two component, thermoset, low odor, 100% solids epoxy designed as an all-purpose coating system for a variety of substrates. It is suited for embedding chip and quartz and is part of the KOSTER Chip and Quartz Floor system. KOSTER MPE-Color can also be used for finish top coats over natural quartz. It can be modified with a range of additives to enhance performance, such as skid resistance, slip resistance, abrasion resistance, and microbial resistance.

Technical Data

Property	Data	
Percentage solids by weight	100%	
Mix Ratio (by volume)	A (resin) : B (hardener)	
	2 : 1	
Viscosity, 70°F	450 cps	
Pot life, 70°F	approx. 40 min	
Dry Time, 70°F	approx. 8 h	
Working Time, 70°F	approx. 20 min	
VOCs	0	
Property	Test Method	Result
Hardness (Shore D)	ASTM D-2240	75-80
Compressive Strength	ASTM D-695	17,000 psi
Tensile Strength	ASTM D-638	4000 psi
Tensile Elongation	ASTM D-638	7.5%
Adhesion to Concrete	ASTM D-4541	400 psi, Concrete Failure
Impact Resistance	ASTM D-2794	>160
Water Absorption	ASTM D-570	0.04%
Flame Spread	ASTM E-648-14	Class I, NFPA 101
Abrasion Resistance	ASTM D-4060	30 mg loss
Coefficient of Friction	ASTM D-2047	0.7 (wet) 0.8 (dry)
Gloss (60 Degrees)	ASTM D-523	100

Fields of Application

- Laboratories
- Garages
- Pharmaceutical Plants
- Clean rooms
- Kitchens
- Hospitals
- Kennels

Substrate

Substrates must be sound, solid, profiled to at least an ICRI CSP2, and free of materials or contaminants that may act as bond breakers. The substrate must be primed with KOSTER ES. Refer to the respective data sheet.

Application

Over textured floor: Apply material using flat squeegee, then back roll and cross roll.

Over smooth floor: Apply material using flat squeegee or notched squeegee to desired thickness; follow by back rolling and cross rolling. Standard systems designs are:

- single broadcast application of KOSTER Color Quartz or KOSTER Color Chips into a pigmented KOSTER MPE-Color body coat with a transparent KOSTER MPE seal coat and a transparent KOSTER UTC top coat.

- single broadcast application of natural quartz into a pigmented KOSTER MPE-Color body coat with a pigmented KOSTER MPE-Color seal coat and a transparent KOSTER UTC top coat.

- double broadcast application of KOSTER Color Quartz or KOSTER Color Chip into transparent KOSTER MPE body coats with a transparent KOSTER MPE seal coat and a transparent KOSTER UTC top coat (refer to KOSTER MPE data sheet).

For KOSTER Chip Floor or KOSTER Quartz Floor as single broadcast application:

1. Apply a coat of mixed KOSTER MPE-Color at approx. 100 sq ft/gal with a flat squeegee. Back roll and cross roll with a 3/8-in epoxy rated non-shed roller. Along edges, the material can be brush applied. Allow 5 minutes for the epoxy to flow and level before broadcast.

2. Broadcast KOSTER Color Chip or KOSTER Color Quartz into the fresh, wet KOSTER MPE-Color coat. Wearing spiked shoes, walk on the wet epoxy holding a suitable container and broadcast chip or quartz into the fresh coating to rejection. Throw the aggregate into the air so that it falls vertically onto the floor. It may take 15 to 30 seconds for the quartz to be absorbed by the epoxy. Do not broadcast into the edge that will be joined into the next section. Leave a 2 ft wide wet edge without broadcast to permit overlapping when proceeding onto next section. Do not walk on the broadcast chip or quartz with spiked shoes. Be sure to keep contaminants out of the chip or quartz. Allow to cure.

3. Sweep off the excess chip or quartz using a stiff, clean, dry broom with synthetic bristles.

4. Lightly sand the chip or quartz surface to remove high spots. Sweep or vacuum the floor to remove all loose particles.

5. Install a seal coat over the chip or quartz broadcast. Broadcast medium and desired texture will affect the coverage of seal coat(s). More material will be required with a coarser broadcast medium or if a smoother finish is desired. Less material will be required with a finer broadcast medium or if a rougher finish texture is desired.

For an abrasion-resistant, UV-resistant, textured surface, apply KOSTER UTC. If UV-resistance and high abrasion resistance are not required, KOSTER MPE can be applied as a top coat. An additional MPE top coat can be applied to achieve a smooth surface. KOSTER UTC can be applied to the smooth surface for additional abrasion and UV-resistance.

For single broadcast application of natural quartz into a pigmented body coat:

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.

1. Apply a coat of mixed KOSTER MPE-Color at approx. 100 sq ft/gal with a flat squeegee. Back roll and cross roll with a 3/8-in epoxy rated, non-shed roller. Along edges, the material can be brush applied.
2. Broadcast natural quartz into the fresh, wet KOSTER MPE-Color coat. Wearing spiked shoes, walk on the wet epoxy holding a suitable container and broadcast quartz into the fresh coating to rejection. Throw the aggregate up into the air so that it falls vertically onto the floor. It may take 15 to 30 seconds for the quartz to be absorbed by the epoxy. Do not broadcast into the edge that will be joined into the next section. Leave a 2 ft wide wet edge without broadcast to permit overlapping when proceeding onto next section. Do not walk on the broadcast quartz with spiked shoes. Be sure to keep contaminants out of the quartz. Allow to cure.
3. Sweep off the excess quartz using a stiff, clean, dry broom with synthetic bristles.
4. Lightly sand the quartz surface to remove high spots. Sweep or vacuum the floor to remove all loose particles.
5. Install a KOSTER MPE-Color seal coat over the quartz broadcast. Broadcast medium and desired texture will affect the coverage of seal coat(s). More material will be required with a coarser broadcast medium or if a smoother finish is desired. Less material will be required with a finer broadcast medium or if a rougher finish texture is desired.
6. For an abrasion-resistant, UV-resistant, textured surface, apply KOSTER UTC. If UV-resistance and high abrasion resistance are not required, KOSTER MPE can be applied as a top coat. An additional MPE top coat can be applied to achieve a smooth surface. KOSTER UTC can be applied to the smooth surface for additional abrasion and UV-resistance.

If KOSTER MPE is to be installed over a self-leveling underlayment or screed, the substrate must be primed with at least one coat of KOSTER ES to prevent outgassing or other inconsistencies in finished appearance. Inspect the substrate for pinholes before coating with KOSTER MPE.

Coverage

Dependent on application.

Base coat: Approx. 160 sq ft/gal (10 mils)

Seal coat(s): Approx. 80-100 sq ft/gal (16-20 mils)

Cleaning

Clean tools immediately with xylene (or similar) after use.

Packaging

CT 263 003	3 gal kit
CT 263 007	7.5 gal kit
CT 263 015	15 gal kit
CT 263 165	165 gal kit

Storage

Store between 50°F and 90°F.

Safety

Follow Safety Data Sheet and the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed.

Warranties

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

Related products

KOSTER EM-VS	Art.-Nr. CT 210 008
KOSTER MPE	Art.-Nr. CT 261
KOSTER MPE-F	Art.-Nr. CT 262
KOSTER UTC	Art.-Nr. CT 321
KOSTER UTC-Color	Art.-Nr. CT 322
KOSTER ES	Art.-Nr. CT 366
KOSTER Color Chips	Art.-Nr. CT 429
KOSTER Color Quartz	Art.-Nr. CT 486 050
KOSTER Skid-Resistant Broadcast-Medium	Art.-Nr. CT 486 055
KOSTER Skid-Resistant Broadcast-Coarse	Art.-Nr. CT 487 055
KOSTER TA Fiber	Art.-Nr. CT 755 044
KOSTER TA Fumed Silica	Art.-Nr. CT 756 053
KOSTER Abrasion Resistant Additive	Art.-Nr. CT 757 007
KOSTER Anti-Microbial Additive	Art.-Nr. CT 759 001
KOSTER Fisheye Eliminating Additive	Art.-Nr. CT 760 010
KOSTER Adhesion Promoting Additive	Art.-Nr. CT 761 001
KOSTER Slip-Resistant Additive	Art.-Nr. CT 762 001
KOSTER Matte Additive	Art.-Nr. CT 763 001

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.