



# **KOSTER Abrasion Resistant Additive**

**Technical Data Sheet CT 757 007** 

Issued: 03-15-21

## Abrasion resistance additive for KOSTER UTC

#### **Features**

KOSTER Abrasion Resistance Additive is a fine, white, crystalline powder that is added into KOSTER UTC and UTC-LT coatings during mixing. The additive greatly increases the abrasion resistance of the cured coating. The additive is high strength, wear-resistant, and possesses a strong ability to resist chemical attacks at extreme temperatures.

#### **Technical Data**

Color White Bulk density 116 lb/ft<sup>3</sup>

Hardness KNOOP = 2000; MOH = 9

Melting point 2,000°C

#### Fields of Application

Use KOSTER Abrasion Resistant Additive where demands on the abrasion resistance of the floor coating are higher than average, such as areas with high vehicle traffic or areas that are constantly scrubbed.

#### Application

KOSTER Abrasion Resistant Additive is added into KOSTER UTC at a rate of 8 oz/gallon of UTC during mixing, immediately after the Acomponent has been added into the B-component. Mix and install KOSTER UTC according to the KOSTER UTC data sheet.

#### Coverage

1/2 pint per gallon of mixed material

#### **Packaging**

CT 757 007 1 quart

#### Storage

Store dry.

### Safety

Consult Safety Data Sheet. Always wear proper personal protective equipment when handling this product.

## **Limited Warranty**

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF

THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

#### Related products

KOSTER MPE	ArtNr. CT 261
KOSTER MPE-F	ArtNr. CT 262
KOSTER MPE-Color	ArtNr. CT 263
KOSTER MPE-F-Color	ArtNr. CT 264
KOSTER UTC	ArtNr. CT 321
KOSTER UTC-Color	ArtNr. CT 322
KOSTER ES	ArtNr. CT 366
KOSTER Color Chips	ArtNr. CT 429
KOSTER Color Quartz	ArtNr. CT 486 050
KOSTER Skid-Resistant Broadcast-	ArtNr. CT 486 055
Medium	
KOSTER Skid-Resistant Broadcast-	ArtNr. CT 487 055
Coarse	
KOSTER TA Fiber	ArtNr. CT 755 044
KOSTER TA Fumed Silica	ArtNr. CT 756 053
KOSTER Anti-Microbial Additive	ArtNr. CT 759 001
KOSTER Fisheye Eliminating Additive	ArtNr. CT 760 010
KOSTER Adhesion Promoting Additive	ArtNr. CT 761 001
KOSTER Slip-Resistant Additive	ArtNr. CT 762 001
KOSTER Matte Additive	ArtNr. CT 763 001

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.