



# **KOSTER Fisheye Eliminating Additive**

**Technical Data Sheet CT 760 010** 

Issued: 05-19-16

# Additive for KOSTER ES and MPE coatings to prevent fisheyes

### **Features**

KOSTER Fisheye Eliminating Additive is an inorganic polymer liquid additive that is formulated to improve the flow of KOSTER ES, MPE and MPE-LT coating systems. The additive decreases fisheyes and the formation of surface abnormalities by decreasing the surface tension and improving wetting of the substrate.

## **Fields of Application**

Use KOSTER Fisheye Eliminating Additive in coatings on substrates that were prepared by grinding, substrates which were lightly contaminated with silicone, oil or other deleterious materials, and on existing epoxy and urethane floors of unknown origin. Facilities where KOSTER Fisheye Eliminating Additive is commonly used in application are machine shops, body shops, automobile prep/delivery areas, and plastics processing facilities. On oil contaminated substrates, KOSTER Fisheye Eliminating Additive is not a substitute for using the KOSTER ORS System. Prior to coating an oil contaminated substrate, the contamination should be removed using the KOSTER ORS system.

#### Application

KOSTER Fisheye Eliminating Additive should be added sparingly to KOSTER MPE or KOSTER ES. A small amount of this additive will not disturb the proper ratio of the hardener and resin blend. Add 3/4 - 1 ½ fl.oz per 1 ½ gallon of blended epoxy and mix well. Reduce amount of KOSTER Fisheye Eliminating Additive dosage for second coat if needed.

#### Coverage

3/4 to 1 ½ fl.oz per 1 ½ gal of blended KOSTER MPE or ES.

# **Packaging**

CT 760 010 1 gal can

# Storage

Store dry.

# Safety

Consult Safety Data Sheet. Always wear proper personal protective equipment when handling this product.

### **Limited Warranty**

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO

OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

#### Related products

riolatou producto	
KOSTER MPE	ArtNr. CT 261
KOSTER MPE-F	ArtNr. CT 262
KOSTER MPE-Color	ArtNr. CT 263
KOSTER MPE-F-Color	ArtNr. CT 264
KOSTER UTC	ArtNr. CT 321
KOSTER UTC-Color	ArtNr. CT 322
KOSTER UTC-LT	ArtNr. CT 323
KOSTER UTC-LT-Color	ArtNr. CT 324
KOSTER ES	ArtNr. CT 366
KOSTER Color Chips	ArtNr. CT 429
KOSTER Color Quartz	ArtNr. CT 486 050
KOSTER Skid-Resistant Broadcast-Medium	ArtNr. CT 486 055
KOSTER Skid-Resistant Broadcast-Coarse	ArtNr. CT 487 055
KOSTER TA Fiber	ArtNr. CT 755 044
KOSTER TA Fumed Silica	ArtNr. CT 756 053
KOSTER Abrasion Resistant Additive	ArtNr. CT 757 007
KOSTER Anti-Microbial Additive	ArtNr. CT 759 001
KOSTER Adhesion Promoting Additive	ArtNr. CT 761 001
KOSTER Slip-Resistant Additive	ArtNr. CT 762 001
KOSTER Matte Additive	ArtNr. CT 763 001

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.