



# KOSTER Slip-Resistant Additive

## Additive to improve slip-resistance of KOSTER UTC/UTC-LT topcoats

### Features

KOSTER Slip-Resistance Additive is a micronized polypropylene polymer additive that increases the slip resistance of KOSTER UTC and UTC-LT topcoats, especially in wet environments. This product is best suited for interior foot traffic areas. It is mixed directly into the resin just before application.

- Increases the durability of coatings
- Increases abrasion-resistance of coatings
- Well suited for wet areas

### Application

For best results, KOSTER Slip-Resistant Additive should only be used in the final topcoat layer of the flooring system. Follow the mixing instructions on the data sheet of the KOSTER topcoat being installed and add KOSTER Slip-Resistant Additive while mixing the A and B components. After adding KOSTER Slip-Resistant Additive, mix well for a minimum of 30 seconds. Apply according to the application instructions on the data sheet of the topcoat.

### Coverage

Add between 1 and 3 fl oz. of KOSTER Slip-Resistant Additive per gallon of mixed KOSTER product.

### Packaging

CT 762 001	1 lb bucket
CT 762 003	3.5 lb bucket

### Storage

Store dry.

### Safety

Consult Safety Data Sheet. Always wear proper personal protective equipment when handling this product.

### Limited Warranty

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities

associated with it.

### Related products

KOSTER MPE	Art.-Nr. CT 261
KOSTER MPE-F	Art.-Nr. CT 262
KOSTER MPE-Color	Art.-Nr. CT 263
KOSTER MPE-F-Color	Art.-Nr. CT 264
KOSTER UTC	Art.-Nr. CT 321
KOSTER UTC-Color	Art.-Nr. CT 322
KOSTER UTC-LT	Art.-Nr. CT 323
KOSTER UTC-LT-Color	Art.-Nr. CT 324
KOSTER ES	Art.-Nr. CT 366
KOSTER Color Chips	Art.-Nr. CT 429
KOSTER Color Quartz	Art.-Nr. CT 486 050
KOSTER Skid-Resistant Broadcast-Medium	Art.-Nr. CT 486 055
KOSTER Skid-Resistant Broadcast-Coarse	Art.-Nr. CT 487 055
KOSTER TA Fiber	Art.-Nr. CT 755 044
KOSTER TA Fumed Silica	Art.-Nr. CT 756 053
KOSTER Abrasion Resistant Additive	Art.-Nr. CT 757 007
KOSTER Anti-Microbial Additive	Art.-Nr. CT 759 001
KOSTER Fisheye Eliminating Additive	Art.-Nr. CT 760 010
KOSTER Adhesion Promoting Additive	Art.-Nr. CT 761 001
KOSTER Matte Additive	Art.-Nr. CT 763 001

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.