



KOSTER IN 7

Technical Data Sheet IN 270

Issued: 03-03-21

Elastic polyurethane-injection foam for sealing water-bearing cracks and joints

Features

KOSTER IN 7 is a polyurethane prepolymer used with 10% catalyst. The product reacts when it comes into contact with water and forms a compact, visoplastic, waterproof polyurethane foam. KOSTER IN 7 remains viscoplastic after reacting and follows crack movements to seal permanently without the necessity of subsequent injections. KOSTER IN 7 is solvent-free and resistant to hydrolysis.

Technical Data

Mixed viscosity, 77°F Approx. 300 cps Volume expansion Max. 1:30 Approx. 9.18 lb/gal Mixed density, 70°F Density of fully cured foam Approx. 0.83 lb/gal Elongation (ASTM D-3574) 100% Tensile strength (ASTM D-3574) 210 psi Shear strength (ASTM C-273) 42 psi Starting time at water contact Approx. 30 sec Approx. 60 sec Expansion time Non-sticky after Approx. 2 min Pot life (no water contact) > 6 h

Fields of Application

Mixing ratio, by weight (A:B) Mixing ratio, by volume (A:B)

KOSTER IN 7 is intended for the single injection sealing of water bearing cracks in concrete and masonry using pressurized injection systems without requiring subsequent injection with a solid body resin.

10:1

12:1

Application

Before injection, seal cracks using KOSTER KB-Fix 5. The minimum application temperature is 40°F. Bring the material up to 60°F before mixing and injection. Temperatures above 77°F will increase reaction rate and reduce pot life. Perform injection using a conventional single component injection pump such as the electrical KOSTER 1C Injection Pump. Drill holes on alternating sides along the course of the crack at an interval of approx. 4 – 6 inches. Insert injection packers into the holes and (when possible) inject from bottom to top. The diameter of the drill holes depends on the injection packers chosen.

Cleaning

Clean tools immediately after use with KOSTER KB-Pur Cleaner.

Packaging

IN 270 005 5.5 kg combipackage IN 270 027 60.5 lb combipackage

Storage

Store the material between 50°F and 90°F. The material can be stored

in originally sealed packages for 6 months.

Safety

Consult Safety Data Sheet. Wear protective gloves and goggles when processing the material. When carrying out injection work, protect the surrounding work area from injection resin that may be discharged from the wall, packers, or drill holes. Do not stand directly behind the packers during injection.

Limited Warranty

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

Related products

ArtNr. C 515 015
ArtNr. IN 900 010
ArtNr. IN 903 001
ArtNr. IN 915 001
ArtNr. IN 929 001
ArtNr. IN 953 002

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.