



KOSTER FS Primer 2C

Two component bonding agent for KOSTER Joint Sealant FS-V and FS-H

Features

KOSTER FS-Primer 2C is a fast-curing, transparent, solvent-free, two component bonding agent. It is used as primer for KOSTER Joint Sealant FS-H and FS-V.

Technical Data

Density, 70°F	Approx. 9.18 lb/gal
Curing time	Approx. 3 hours
Application of next layer	After 30 – 180 min
Working time, 70°F	Approx. 20 min

Fields of Application

KOSTER FS-Primer 2C is a bonding agent for polysulfide-based joint sealants, designed for sealing and waterproofing construction joints.

Substrate

The substrate must be dry and free of silicone, loose particles, oil and grease. For cleaning substrates, we recommend the use of dirt and grease-solving water and solvent-based cleaning agents. If necessary, hot steam clean, lightly grind, or roughen by sandblasting.

Application

Mix the components intensively until a homogeneous consistency is reached. Apply KOSTER FS Primer 2C at ambient and substrate temperatures between 40°F and 90°F. KOSTER FS-Primer 2C is brush applied in a thin layer. After a minimum curing time of approx. 30 min, apply KOSTER Joint Sealant FS-H or FS-V. Be sure that no dust or other contaminants come into contact with the primed surface.

Coverage

Dependent on application.

By weight:

Approx. 0.7 - 1.4 lb/100 ft of joint.

By volume:

Approx. 20 fl oz /100 ft of joint.

Consumption varies depending on roughness and porosity of the substrate, and width of the joint flanks.

Cleaning

Clean tools immediately after use with KOSTER Universal Cleaner.

Packaging

J 139 200 200 g combi package

Storage

Store the material between 40°F and 90°F.

Safety

Follow Safety Data Sheet for proper personal protective equipment to use when handling this product. Use only as directed. Wear solvent-resistant gloves and goggles when working with the material. Ventilate the workspace well.

Limited Warranty

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

Related products

KOSTER Joint Sealant FS-V	Art.-Nr. J 231
KOSTER Joint Sealant FS-H	Art.-Nr. J 232
KOSTER KD System	Art.-Nr. W 219
KOSTER Universal Cleaner	Art.-Nr. X 910 010

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.