



KOSTER Joint Sealant FS-H grey

Self-leveling, elastic, 2 component poly-sulfide joint sealant

Features

KÖSTER Joint Sealant FS-H Grey is an elastic, poly-sulfide, pourable joint sealant used to seal horizontal joints. When fully cured, KÖSTER Joint Sealant FS-H Grey is a rubber-elastic sealant with a high mechanical load capacity, good resistance to ground water, sea water, salt solutions, and mineral oils.

Technical Data

Mixing ratio (by weight)	100 : 8 (A : B)
Working time (70F, 50% RH)	Approx. 2 hrs
Curing time	Approx. 24 hrs
Shore A-hardness	approx. 35
Retraction capacity	≥ 80%
Total deformation permitted	Approx. 25%
Application temperature	40-105 °F

Fields of Application

KÖSTER Joint Sealant FS-H Grey can be used to permanently and elastically seal horizontal joints in below grade construction, cracks in basements, foundations of buildings, joints in sewage treatment plants, garages, and tunnels.

Application

The flanks of the joint must be clean, solid, and free of grease and dust. Prime absorbent substrates twice with KÖSTER FS-Primer; prime non-porous substrates once with KÖSTER FS Primer. Do not prime substrates coated with KÖSTER VAP I 2000 vapor barriers. Mix components thoroughly using a slow speed mixer for at least 3 minutes, until a homogeneous consistency is reached. Approx. 2 hours after priming, apply KÖSTER Joint Sealant FS-H Grey with a caulking gun, trowel, or spatula, or by pouring.

Coverage

Joint width (in)	3/8	1/2	3/4	1	1-3/16	1-3/8
Thickness of joint sealant (in)	5/16	3/8	1/2	9/16	3/4	13/16
Coverage (ft/gal)	150	80	50	32	23	18

Cleaning

Clean tools immediately after use with KÖSTER KB-Pox Cleaner.

Packaging

J 234 004 8.8 lb combipackage

Storage

Store in a cool, dry place. In original unopened container, the material can be stored for a minimum of 6 months.

Safety

Consult Safety Data Sheet. Always wear proper personal protective equipment when handling this product.

Limited Warranty

KÖSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KÖSTER covenants that in the event any of its products fail to meet their published specifications, KÖSTER shall replace those products proved to be defective. KÖSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KÖSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KÖSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

Related products

KÖSTER FS Primer 2C	Art.-Nr. J 139 200
KÖSTER Joint Sealant FS-V	Art.-Nr. J 231
KÖSTER Joint Sealant FS-H	Art.-Nr. J 232
KÖSTER Joint Sealant FS-V Grey	Art.-Nr. J 233
KÖSTER Universal Cleaner	Art.-Nr. X 910 010

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.