



KOSTER Crisin 76 Cream

Solvent-free resin/silane injection cream against rising damp in walls

Features

KOSTER Crisin 76 Cream is a solvent free resin/silane injection cream against capillary rising moisture in walls.

Technical Data

Density	0.03 lb/cu in
Solids content	Approx. 85 %
Application temperature	40-95 °F

Fields of Application

KOSTER Crisin 76 Cream is a retroactive DPC (Damp Proof Course) waterproofing against capillary rising moisture. It can be applied from inside or outside of the building. It can be applied in cases of high degrees of moisture penetration (95% +/- 5% saturation) and salt contamination.

Application

Drill horizontal holes (14 mm diameter) in the lowest masonry joint to a depth of 1 1/2-in. less than the wall thickness. Clean the holes by flushing with water or compressed air. Drill holes 4 in. apart independent of wall thickness. Inject KOSTER Crisin 76 Cream from the cartridge with the KOSTER Hand Pistol fitted with an injection tube. Seal the holes immediately with KOSTER KB Fix 5 flush with the wall. When using self-priming injecting equipment, use the 2.64 gallon buckets to refill the cartridge.

Coverage

Dependent on application.

Wall thickness (cm)	Consumption (ml/m)	Yield/310 ml cartridge	Yield/530 ml cartridge
12	Approx. 140	2.2 m	3.8 m
24	Approx. 330	0.9 m	1.6 m
36	Approx. 510	0.6 m	1.0 m

Cleaning

Clean tools immediately after use with water.

Packaging

M 278 006	6 x 310 ml box
M 278 010	2.64 gallon bucket
M 278 012	12 x 310 ml box
M 278 310	310 ml cartridge
M 278 600	12 x 600 ml box

Storage

Store at room temperature. In originally sealed packaging, the material can be stored for 12 months.

Safety

Consult Safety Data Sheet. Always wear proper personal protective

equipment when handling this product.

Limited Warranty

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

Related products

KOSTER KB-FIX 5	Art.-Nr. C 515 015
KOSTER Polysil TG 500	Art.-Nr. M 111
KOSTER Fine Plaster	Art.-Nr. M 655 025
KOSTER Restoration Plaster 1 Grey	Art.-Nr. M 661 025
KOSTER Restoration Plaster 2 White	Art.-Nr. M 662 025
KOSTER Restoration Plaster 2 "Fast"	Art.-Nr. M 663 030
KOSTER Restoration Plaster 2 "Light"	Art.-Nr. M 664 025

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.