



KOSTER Façade Cream

Water repellent façade-hydrophobing cream for cementitious-based building materials

Features

KOSTER Façade Cream is a high-grade façade impregnation for brick, natural stone and cementitious building materials. Due to its high resistance against alkalinity it is also suitable for application to fresh cementitious substrates. The creamy, stable consistency and the resulting processibility with brush or roller reduce the drip spraying losses to a minimum.

KOSTER Façade Cream protects buildings from driving and normal rain water; is water vapor permeable; and is resistant to frost and de-icing salts.

Technical Data

Color	Milky, creamy white (transparent after drying)
Active ingredient	Polysiloxane, solvent-free
Content of active ingredient	25 %
Viscosity	3000 cps
Application temperature	41 °F to 86 °F
Rainproof	after approx. 20 min (68 °F)
Density	8.35 lb/gal
Flash point	> 212 °F

Fields of Application

KOSTER Façade Cream is suitable for making absorbent masonry and cementitious substrates water repellent such as brick, non-glazed clinker and facing stones, plasters, mortars, as well as lime stones and natural stones.

Substrate

The surface must be dry or slightly damp, clean and free of cracks wider than 0.01 inch (0.3 mm) and free of voids. Crusts made up of contaminants or damaging salts must be removed prior to applying the material. Paints or other coatings must be completely removed as well as any cleaning agent residues. Damaged or missing joints must be broken out and re-pointed prior to the application of KOSTER Façade Cream.

Non-absorbent substrates e.g. marble or glazed brick are not suitable for use with the KOSTER Façade Cream.

Application

KOSTER Façade Cream is applied in one work-step by brushing, rolling or spraying (with an airless spraying device) the material onto the prepared substrate. Cover up areas which will not be waterproofed e.g. doors, windows etc. with plastic sheeting.

Under certain circumstances, the application of KOSTER Façade Cream may lead to an intensification of the hue of the substrate. An initial test should be carried out on a small test area of approx. 10 ft².

Coverage

Approx. 160-400 sq ft/gal, depending on absorbency of the substrate. Apply product to a test area prior to the main installation in order to determine the coverage and the effect of the product.

Cleaning

Clean tools immediately after use with water.

Packaging

P 200 005	1.32 gal pail
P 200 015	15 l bucket

Storage

Store in a cool, dry place. Protect from freezing. In originally sealed packages, the material may be stored for 1 year.

Safety

Limited Warranty

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

Related products

KOSTER Restoration Plaster White	Art.-Nr. M 662 025
KOSTER Façade Cleaning Cream	Art.-Nr. P 110 005
KOSTER Siloxan	Art.-Nr. P 240 010

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.