



KOSTER SC

Skimcoat patch underlayment

Features

KOSTER SC is a high quality, fast curing skimcoat underlayment that provides a smooth, level surface ready to receive flooring systems. It may be applied over KOSTER VAP I 2000 coatings and concrete. KOSTER SC accepts all major floor coverings and is compatible with most adhesives. If the material is installed onto smooth, non-absorbent substrates such as KOSTER VAP I 2000 coatings, the substrate must be primed with KOSTER VAP I 06 Primer.

Technical Data

Property	Data
Compressive Strength	≤ 3500 psi (ASTM C109)
Flexural Strength	≤ 1500 psi (ASTM C348)

Fields of Application

KOSTER SC is designed to provide a smooth and level surface of plain concrete surfaces as well as surfaces coated with KOSTER VAP I 2000 moisture control coatings. It is intended for interior use.

Substrate

Concrete substrates to receive KOSTER SC must be sound, clean and absorptive, free of curing agents, oil, grease, paint, loose particles or any other contaminant that may weaken the bond. The pull off strength of the substrate must be at least 215 psi. Do not acid etch substrates. Do not clean substrate with chemicals. Do not apply over adhesive residue. Do not bridge expansion joints with KOSTER SC. Expansion joints must be installed accordance with local building codes.

Application

Plain concrete without KOSTER VAP I 2000 coating

Concrete substrates are prepared by shot blasting, or grinding in order to achieve an absorbent, open pored substrate. No primer is required over concrete.

Concrete coated with KOSTER VAP I 2000 coating

The properly installed and fully cured KOSTER VAP I 2000 coating is primed using KOSTER VAP I 06 Primer (coverage: 650-800 sq ft/gal). For further information, refer to the data sheet of the KOSTER VAP I 06 Primer.

Mixing

Add 2.5-2.75 quarts of clean, cool, potable water into a clean mixing vessel. Do not overwater. Add the 10 lb bag of KOSTER SC while mixing with an electrical mixer (650 rpm). After all material has been added, mix for 2-3 minutes. The resulting consistency should be lump free. Material can also be mixed at a ratio of 1 part water to 2 parts KOSTER SC, by volume.

Installation

Apply the mixed material by trowel to the desired thickness. KOSTER

SC can be installed between 1/8 and 1/2-in. The material will set within 10-15 minutes. After initial set, remove all overlap marks, seams, and inconsistencies by smoothing with a steel trowel. Material can be walked on after 15-20 minutes, depending on thickness and ambient conditions. Finish flooring systems can be applied within 30 minutes depending on thickness, ambient conditions, and flooring system.

Coverage

Approx. 35 sq ft/10 lb bag at 1/8-in

Cleaning

Use water to clean all tools immediately after use.

Packaging

SL 282 022 10 lb bag

Storage

Store in a cool, dry place.

Safety

Consult Safety Data Sheet. Contains Portland cement and silica sand; avoid contact with eyes or prolonged contact with skin. Do not take internally. Eliminate exposure and avoid breathing dust; contains free silica. Wear personal protective equipment including gloves and safety eyewear. In case of eye contact, flush immediately with water and consult a physician. In case of skin contact, wash immediately with soap and water.

Limited Warranty

KOSTER warrants that its product shall be in accordance with the specifications published in the current revision of the products data sheet. KOSTER covenants that in the event any of its products fail to meet their published specifications, KOSTER shall replace those products proved to be defective. KOSTER shall not be responsible for any incidental or consequential damages due to the breach of its warranties. Notwithstanding the foregoing, KOSTER's sole liability hereunder shall not exceed the cost of the defective product originally purchased. EXCEPT AS SET FORTH ABOVE, KOSTER MAKES NO OTHER WARRANTIES EXPRESS OR IMPLIED AND MAKES NO WARRANTY AS TO THE MERCHANTABILITY OR FITNESS OF THE PRODUCT FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The user must determine if the product is suited for the intended use and the user must bear the risks and liabilities associated with it.

Related products

KOSTER VAP I 2000 Zero VOC	Art.-Nr. CT 230
KOSTER VAP I 06 Primer	Art.-Nr. SL 131 009

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The installer is responsible for the correct application taking into consideration the specific conditions of the construction site and the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which deviate from the specifications contained in any Company literature may not be relied upon in the absence of written confirmation from the Company. The installer must comply with all testing, technical requirement, guidelines, and industry customs at all times. The terms, conditions, and limitations contained in the written warranty for the product controls over the specifications contained herein. This guideline has been technically revised; all previous versions are invalid.